



TECHNICAL DATA SHEET - DIGITAL PRINTING - PVC - PERMANENT ADHESIVE V201TR1

Film composed of an $80-\mu m$, calendered, polymeric PVC, which is coated with a pressure-sensitive acrylic adhesive. For solvent, eco-solvent, latex and UV inkjet printing. White translucent surface finish.

FILM FEATURES:

	•	. •		1
nd	ייוו	ナハノム	Va	LIDC
IIIU	ııca	tive	٧a	ues

• Thickness (μm): 80

Total thickness of the product (µm):

Average values

Average values

Standard

HEXGSM001

Tensile Strength (N/25 mm): min. 35 HEXNFX41021

Elongation at break (%): min. 100 HEXNFX41021

Shrinkage 168 hours at 70 °C (158 °F) (mm): < 0.4 HEXRET001

GENERAL PRINTER COMPATIBILITIES:

	Solvent	Eco-solvent	Latex	UY
V20ITRI	✓	✓	✓	✓

LINER:

- Silicone-coated PE paper 145 g/m² with light grey HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

	<u> </u>	<u>Average values</u>	<u>Standard</u>
•	Peel strength test 180° on glass (N/25	HEXFTM001	
	after 20 minutes of application	´ 18	
	after 24 hours of application	22	
•	Initial tack (N/25 mm):	18	HEXFTM009
•	Release (N/25 mm):	0.2	HEXFTM003

Resistance to solvents: the adhesive is resistant to most chemicals (alcohol, diluted acids, oils).

ADHESIVE:

- Solvent-based acrylic adhesive.
- Adhesion is immediate and permanent (non-repositionable adhesive), suitable for wet application.

USER'S INSTRUCTIONS:

- Touch-dry after less than 15 minutes depending on printer used.
- Recommended minimum application temperature: +10 °C (+50 °F).
- Operating temperature range (outdoors): -40 °C to +90 °C (-40 °F to +194 °F).
- Very good adhesion to glass, steel, aluminium, PVC, melamine, etc. <u>except grain substrates</u> or <u>substrates coated with acrylic paint.</u>
- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.

OPERATING RECOMMENDATIONS:

- Optimal drying time for the inks before laminating, coating or further processing is 24 hours minimum.
- The surface finish of your printings may be modified/improved/protected by applying the appropriate laminate: V750 or PC500. For UV printings, use the protective VCR750 laminate.

STORAGE:

• Shelf life (before application):

The shelf life of this film is I year when stored upright in its original packaging in a dust-free environment at a temperature ranging from +15 °C to +25 °C (+59 °F to +77 °F) with relative humidity of 50 %.

DURABILITY: (Central European climate)

Vertical outdoor exposure:

Unprinted: 5 years.

Printed and laminated:

- PC500: 5 years;
- V750: 4 years;
- VCR750: 3 years.

Printed: 2 years.

To find the indicative durabilities of the films for any other exposure and geographical area, please refer to the "Conversion rules for indicative durabilities according to geographical area" chart available under Durability, on the "Professionals" pages on our site www.hexis-graphics.com.

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. The measuring methods for the standards quoted above served as the basis for the development of our own measuring methods, which are available on request. Please feel free to contact us to get the latest instructions in use. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.